



HAND MADE, HAND TUFTED

QUALITY CODE: HT-550

TECHNICAL PRODUCT SPECIFICATION

PHYSICAL CHARACTERISTICS

- ~ YARN CONTENT (ISO 1833)
- ~ YARN COUNT (ISO 2060)
- ~ YARN TWIST
- ~ PILE HEIGHT (BS4223)
- ~ TOTAL HEIGHT
- ~ PILE WEIGHT
- ~ TOTAL WEIGHT
- ~ NUMBER OF ROWS (BS4223)
- ~ NUMBER OF STITCHES (BS4223)
- ~ DENSITY
- ~ LATEX
- ~ DYE METHOD
- ~ DYE CONTENTS
- 100% FINE NEW ZEALAND WOOL
- 260 TEX/2.6NM
- +/- 140TPM
- +/- 8 MM
- +/- 13 MM
- +/- 3000GM PER M2 (+/- 5.87LB/YARD2, 94OZ/YARD2)
- +/- 4300GM PER M2 (+/-8.07LB/YARD2, 130OZ/YARD2)
- +/- 28 PER 10CM (+/-7.1 PER INCH)
- +/- 21 PER 10CM (+/-5.3 PER INCH)
- +/- 588 TUFTS PER 1DM2 (+/-38 PER INCH2)
- NATURAL RUBBER/SYNTHETIC
- SKEIN DYEING
- CLARIANT, BASF AND COLOUR TEX

PRODUCT SPECIFICATIONS

- ~ CARPET PILE ABRASION (WIRA) BSEN1813
- ~ CHANGE IN SURFACE STRUCTURE (HEXAPOD TUMBLER)
- A) AFTER 1500 CYCLES
- B) AFTER 8000/12000 CYCLES
- ~ ISO/PAS 11856-SECTION5 (FIBER SHEDDING)
- A) AFTER 10,000 RUBS
- B) AFTER 30,000 RUBS
- ~ TUFT WITHDRAWL FORCE (ISO4919)
- ~ TOTAL VOLATILE ORGANIC COMPUNT (TVOC)
- ~ COLOUR FASTNESS
- A) TO WATER (ISO105 E01)
- B) TO LIGHT (ISO105 B02)
- C) TO RUBBING (ISO105X12)
- D) TO SHAMPOOING (BS1006UKTB)
- E) TO PVC (ISO105 X 10)
- +/- 63.36MG PER 1000 CYCLES
- +/- 4 (PASS)
- +/- 3 (PASS)
- +/- 159 MG
- +/- 193 MG
- +/- 28 NEWTON
- PASS
- 4
- 6
- 4
- 4
- 4

PRODUCT TREATMENTS

- ~ ANTISTATIC TREATMENT
- ~ FLAMMABILITY (US CPSC 16CFR PART 1630)
- ~ ADDITIONAL AVAILABLE (OPTIONAL)
- PASS
- PASS
- ANTI-MOTH, , MYSTOX CP, ANTI SOIL, LANASHIELD / SCOTCH GUARD,

Art Under Your Feet™



www.kaandlarugs.com



TM Kaandla Rugs Ltd, all rights reserved.

Note Technical specification may slightly vary as rugs are hand made. Specifications quoted are for plain carpets only, these may change as per design and structure.